

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 15/28, 15/60	A1	(11) International Publication Number: WO 96/13282 (43) International Publication Date: 9 May 1996 (09.05.96)
(21) International Application Number: PCT/GB95/02535 (22) International Filing Date: 27 October 1995 (27.10.95) (30) Priority Data: 9421653.8 27 October 1994 (27.10.94) GB (71) Applicant (for all designated States except US): INNOVATIVE TECHNOLOGIES LIMITED [GB/GB]; Road Three, Winsford Industrial Estate, Winsford, Cheshire CW7 3PD (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): QIN, Yimin [GB/GB]; 123 Victoria Road, Northwich, Cheshire CW9 5RQ (GB). GILDING, Keith, Dennis [GB/GB]; Nepenthe, Winsford Road, Wettehall, Winsford, Cheshire CW7 4DL (GB). (74) Agent: ATKINSON, Peter, Birch; Marks & Clerk, Sussex House, 83-85 Mosley Street, Manchester M2 3LG (GB).		(81) Designated States: AL, AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, LS, MW, SD, SZ, UG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: WOUND DRESSING (57) Abstract A wound dressing comprises in combination (i) a first wound contact layer which preferably has a positive effect on the healing of the wound, and (ii) a second layer of greater hydrophilicity than the first layer.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

WOUND DRESSING

The present invention relates to wound dressings.

For the treatment of many types of wounds, particularly medium to highly exuding wounds (e.g. 2nd and 3rd degree burns, decubitus ulcers and leg ulcers) it is necessary to ensure that bulk exudate is removed from the wound and peripheral skin to reduce or eliminate maceration. Prior art dressings have not always proved satisfactory in venting the large amount of exudate present in a wound. As such, the dressing becomes saturated and this results in maceration and excoriation. Additionally, the dressing may require to be changed relatively frequently and this is a labour intensive operation.

According to the present invention there is provided a wound dressing provided in combination

- (i) a first wound contact layer which preferably has a positive effect on the healing of the wound, and
- (ii) a second layer of greater hydrophilicity than the first layer.

Layer (i) is designed to provide a positive action in assisting healing of the wound and may take various forms (as described later) depending on the type of wound to be treated. The provision of layer (ii) (which is of greater hydrophilicity than layer (i)) ensures that exudate present in layer (i) may pass into layer (ii) so as to increase the time before layer (i) becomes saturated. Preferably the hydrophilicity of layer (ii) is at least twice, and more preferably 3 to 5 times, that of layer (i).

Layer (i) (i.e. the wound contact layer) will generally be relatively thin (e.g. 50-1000 microns) and may be such as interact positively with the wound to assist healing thereof. Thus, for example, layer (i) may be one which provides for clotting via agglutination of red cells. Alternatively, the layer may be one which is capable of debriding the wound. A further possibility is for the layer to be one which delivers a component to the wound, e.g. an ion, drug, or anti-microbial agent. Examples of the materials which may be used for layer (i) are as follows:

- (a) calcium alginate which will provide calcium ions for haemostasis;
- (b) zinc alginate to deliver zinc ions into the wound to assist healing;
- (c) silver alginate to deliver silver ions as powerful anti-microbial agents to infected wounds;
- (d) chitosan to provide haemagglutination (i.e. clotting by gelation of red cells leaving the intrinsic and extrinsic clotting cascade intact). Chitosan also appears to have some beneficial effects on contact allergies and anti-microbial activity by stimulating the oxidative attack of white cells. Chitosan has also been reported to assist healing and reduce scarring;
- (e) pectin for stimulating autolysis and wound debridement. The pectin may be provided, for example, as pectin/carboxymethyl cellulose/alginate or pectin/alginate;
- (f) silver N,O-carboxymethyl chitosan or silver O-carboxymethyl chitosan;
- (g) a gauze material prepared as described in our earlier U.K. Patent Application No. 9415828 and incorporating silver ions for delivery to the wound;

(h) a dehydrated hydrogel, e.g. of alginate or chitosan, which is of high integrity when it picks up water.

Layer (i) may be provided as a woven, non-woven or knitted material or as a gel. The layer may be in the form of a "rope" for deep cavities or an amorphous gel for sinuses.

Various species may be incorporated in layer (i) for delivery to the wound, e.g.

simple anti microbial agents (e.g. Zn^{2+} and Ag^{+}) and metal ions which are enzyme cofactors

enzymes such as collagenase and metallo proteases such as plasmin or plasminogen which can be dosed into layer (i) to be released into the wound during healing to aid fibrinolysis and reduce scar formation

drugs, such as anti-inflammatories etc., for dermatological application.

Layer (i) will also capture proteins and growth factors from the wound, initially by adsorption and as this layer hydrates later in the healing process these proteins and growth factors will be delivered back to the healing wound.

Layer (ii) is preferably also of a woven, non-woven or knitted fibrous material, e.g. a felt.

Layer (ii) will generally have a thickness of 1000 to 5000 microns, preferably 1000 to 2500 microns and may comprise

- (a) sodium alginate/calcium alginate felt (e.g. containing 20-60% sodium);
- (b) a sodium calcium carboxymethyl cellulose felt;
- (c) a sodium zinc carboxymethyl cellulose felt;

- (d) a sodium calcium polyacrylate felt; or
- (e) a sodium calcium carrageenin felt.
- (f) an alginate/CMC felt.
- (g) carboxymethyl cellulose (CMC) felt; or
- (h) N,O-carboxymethyl chitosan (NOCC) felt.

The sodium in the above materials may be replaced by potassium.

One particular example of wound dressing in accordance with the invention comprises chitosan as layer (i) and an alginate or alginate/CMC felt as layer (ii).

As explained above, layer (ii) is of greater hydrophilicity than layer (i). The requisite hydrophilicity (rate of exudate absorption) for layer (ii) may be obtained by mixing fibres of varying sodium/calcium ratios (for felts (a), (b), (d), and (e)) and by mixing fibres of varying sodium/zinc ratios (for felt (e)). The absolute capacity of the felt for absorbing exudate may be varied by mixing fibres of varying hydrophilicity. For example the absorption capacity of felts made from CMC, polyacrylate or NOCC, all of which are powerfully hydrophilic, may be lowered by the incorporation of alginate fibres. Alternatively, materials of the requisite absorption capability may comprise alginates co-spun with other polymeric materials as disclosed in our copending U.K. Patent Application No. 9419572.

As an alternative to layers (i) and (ii) both being non-woven, it is possible for layers (i) and/or (ii) to be of other types of material (provided that layer (ii) is more hydrophilic than layer (i)). Examples of such alternative constructions are as follows.

- 5 -

(1) Layer (i) is a non-woven felt and layer (ii) is a hydrogel. An example of such a dressing is one comprising a non-woven felt of chitosan (as layer (i) with a NOCC hydrated hydrogel (as layer (ii)). In such a dressing, the chitosan provides haemostatic and anti-microbial properties and the highly absorbing NOCC provides the exudate handling properties. The exclusive nature of the gel ensures that growth factors and other proteins from the wound remain in layer (i) (i.e. the chitosan layer) for ultimate delivery back to the wound. The dressing is suitable for donor sites and 2nd and 3rd degree burns. Obviously a NOCC hydrated hydrogel may be used in conjunction with other (less hydrophilic) materials as layer (i).

(2) Layer (i) may be comprised of spun hydrocolloid including a mixture of components to produce a product which is a cross between an alginate and a hydrocolloid. Thus, for example, it is possible to spin hydrocolloids from solutions of alginate, gelatin, pectin, and CMC, e.g. in the following amounts.

Alginate	Gelatin	Pectin	CMC
45	10	25	20
35	10	35	20

In this case, the layer (ii) may for example be a material as described in our aforementioned copending U.K. Patent Application No. 9415828, a relatively high sodium or potassium (e.g. 20-60%) calcium alginate, carboxymethyl cellulose or polyacrylic acid/alginate.

Layers (i) and (ii) may be joined together, e.g. by needle punching, or may be applied separately to the wound.

In a highly preferred embodiment of the invention, the dressing comprising layers (i) and (ii) is associated with a breathable film which is of increased MVTR capability in the presence of liquid water as compared to moisture vapour only. MVTR in the presence of liquid water may be measured by ASTM E96BW whereas MVTR in the presence of moisture vapour alone may be measured by ASTM E96B (water method). Preferably the value of the breathability in the presence of liquid water is at least twice and preferably at least three times that in the presence of moisture vapour alone. The value may be up to 30 or 40 times that for moisture vapour alone. Typically the film will be of a material which has an MVTR in the presence of moisture vapour alone (ASTM E96B) of 2,000 to 2,500 $\text{g m}^{-2} \text{24hr}^{-1}$ and an MVTR in the presence of liquid water (ASTM E96BW) in the range 6,000 to 30,000 $\text{g m}^{-2} \text{24hr}^{-1}$ (e.g. 6,000 to 10,000 $\text{g m}^{-2} \text{24hr}^{-1}$). Typically the film will have a thickness of 30-70 microns more preferably 40-60 microns, e.g. about 50 microns.

The film may for example be of polyurethane. Suitable films are available from Innovative Technologies Limited under the designations IT325, IT425 and IT625.

An adhesive will be provided on the film for bonding the latter two the skin around the wound. The adhesive is preferably a hydroactive adhesive most preferably one which, as a continuous layer having a thickness of 20 microns, has an MVTR of 15,000 $\text{g m}^{-2} \text{24hr}^{-1}$ using ASTM E96B. Preferably the combination of the adhesive and film is such as to provide an MVTR of 6,000 to 10,000 $\text{g m}^{-2} \text{24hr}^{-1}$. An example of a

suitable adhesive is a hydroactive adhesive available from Innovative Technologies under the designation ITHA.

The hydroactive adhesive may be provided as a continuous layer on the film. The coating thickness is preferably in the range 15 to 25 microns e.g. about 20 microns.

Alternatively the adhesive may be a pressure sensitive adhesive provided as a cross-pattern to achieve 20-50% area coverage and to achieve similar MVTRs for the combination of adhesive and film of $6,000$ to $10,000 \text{ g m}^{-2} 24\text{hr}^{-1}$.

When the dressing is applied to a wound, the film will generally simply be laid over the combination of layers (i) and (ii).

In use of the dressing comprising such a film, exudate from the wound will initially be absorbed into layer (ii) and will pass therethrough until it comes into contact with the film. The breathability of the film is increased in contact with the liquid present in layer (ii), the increase being dependant on the amount of exudate present in layer (ii) (a greater amount of exudate in layer (ii) producing a greater increase in the breathability of the film). Moisture is therefore able to vent from layer (ii) via the film at a rate which is greater than the MVTR of layer (ii) which is therefore prevented from becoming saturated.

As the wound begins to dry-up during the healing process, the MVTR of the film decreases so that layer (ii) remains moist and does not dry out, thus facilitating healing.

The invention will be illustrated with reference to the following non-limiting Examples.

Example 1

A non-woven felt made of chitosan fibres and a non-woven felt of a calcium/sodium alginate were needled together to form a two-layer dressing. The chitosan felt provides a wound contacting layer which promotes healing of the wound and also provides antimicrobial properties for the dressing. The calcium/sodium alginate felt has a high absorption capacity.

This combined dressing has the wound healing properties of the chitosan felt and the absorbency of the calcium/sodium alginate felt. By drawing the fluid away from the wound surface, the wound is kept in a relatively dry condition thereby eliminating build up of wound exudate and remove skin maceration.

Example 2

A non-woven felt of calcium alginate fibres and a non-woven felt of a calcium/sodium alginate were needled together to form a two-layer dressing. The calcium/sodium alginate contained a minimum of 10% of sodium so as to render it more absorbent than the pure calcium alginate felt.

The calcium alginate fibre was a high M fibre which gels more easily than the high G fibre. On application to a wound, the calcium alginate fibre gels to form a moist protective layer whilst excessive fluid is taken up by the calcium/sodium alginate. The wound is therefore kept in a moist healing environment whilst maceration of healthy

skin is prevented by the removal of excessive fluid to the calcium/sodium alginate fibre (the upper layer).

- 10 -

CLAIMS

1. A wound dressing comprises in combination
 - (i) a first wound contact layer which preferably has a positive effect on the healing of the wound, and
 - (ii) a second layer of greater hydrophilicity than the first layer.
2. A dressing as claimed in claim 1 wherein the hydrophilicity of layer (ii) is at least twice that of layer (i).
3. A dressing as claimed in claim 2 wherein the hydrophilicity of layer (ii) is 3 to 5 times that of layer (i).
4. A dressing as claimed in any one of claims 1 to 3 wherein layer (i) has a thickness of 50 to 1,000 microns.
5. A dressing as claimed in any one of claims 1 to 4 wherein layer (i) is one which provides for clotting via agglutination of red cells.
6. A dressing as claimed in any one of claims 1 to 4 wherein the layer (i) is one which is capable of debriding the wound.

- 11 -

7. A dressing as claimed in any one of claims 1 to 4 wherein layer (i) delivers a component to the wound.

8. A dressing as claimed in any one of claims 1 to 4 wherein layer (i) comprises calcium alginate, zinc alginate, silver alginate, chitosan, pectin, silver N,O-carboxymethyl chitosan, silver O-carboxymethyl chitosan or a dehydrated hydrogel.

9. A dressing as claimed in any one of claims 1 to 8 wherein layer (ii) is a woven, non-woven or knitted fibrous material.

10. A dressing as claimed in any one of claims 1 to 9 wherein layer (ii) has a thickness of 1,000 to 5,000 microns.

11. A dressing as claimed in any one of claims 1 to 10 wherein layer (ii) is a felt comprised of sodium alginate/calcium alginate, sodium calcium carboxymethyl cellulose, sodium zinc carboxymethyl cellulose, sodium calcium polyacrylate or sodium calcium carrageenin.

12. A dressing as claimed in any one of claims 1 to 11 which is associated with a breathable film having an increased MVTR capability in the presence of liquid water as compared to moisture vapour alone.

- 12 -

13. A dressing as claimed in claim 12 wherein the film has an MVTR in the presence of moisture vapour alone of 2,000 to 2,500 $\text{g m}^{-2} 24\text{hr}^{-1}$.
14. A dressing as claimed in claim 12 or 13 wherein the film has an MVTR in the presence of liquid water of 6,000 to 30,000 $\text{g m}^{-2} 24\text{hr}^{-1}$.
15. A dressing as claimed in any one of claims 11 to 15 wherein the film has a thickness of 30-70 microns.
16. A dressing as claimed in anyone of claims 12 to 15 wherein the film is of a polyurethane.
17. A dressing as claimed in any one of claims 12 to 16 wherein an adhesive is provided on the film for bonding the latter to skin around the wound.
18. A dressing as claimed in claim 17 wherein the adhesive is a hydroactive adhesive.
19. A dressing as claimed in claim 18 wherein the adhesive is one which, as a continuous layer having a thickness of 20 microns, has an MVTR of 15,000 $\text{g m}^{-2} 24\text{hr}^{-1}$.

- 13 -

20. A dressing as claimed in any one of claims 17 to 19 where the adhesive is provided as a continuous layer.

21. A dressing as claimed in any one of claims 17 to 20 wherein the thickness of the adhesive is 15 to 25 microns.

22. The combination of a wound dressing as claimed in any one of claims 1 to 11 and a breathable film having an increased MVTR capability in the presence of liquid water as compared to moisture vapour alone.

INTERNATIONAL SEARCH REPORT

International Application No.

PC./GB 95/02535

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L15/28 A61L15/60

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR,A,2 663 229 (BROTHIER LABORATOIRES) 20 December 1991 see claims ---	1
X	EP,A,0 227 955 (UNIV STRATHCLYDE) 8 July 1987 see claims; figure 1 ---	1
A	EP,A,0 431 479 (HOECHST JAPAN) 12 June 1991 see claims ---	1-22
A	EP,A,0 477 979 (SUNFIBRE CO LTD ;UNIV TOTTORI (JP)) 1 April 1992 see claims --- -/--	1-22

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

28 February 1996

Date of mailing of the international search report

12. 03 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 PatentAan 1
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, 71, 31 651 epo nl.
Fax (+ 31-70) 340-3016

Authorized officer

ESPINOSA, M

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 95/02535

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 302 536 (SQUIBB & SONS INC) 8 February 1989 see figure 1; examples -----	1-22

Form PCT ISA:210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC 1/GB 95/02535

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2663229	20-12-91	NONE	
EP-A-0227955	08-07-87	AU-B- 575298	28-07-88
		AU-B- 1724983	31-01-85
		CA-A- 1212879	21-10-86
		DE-A- 3378185	17-11-88
		EP-A,B 0099758	01-02-84
		JP-A- 59082855	14-05-84
EP-A-0431479	12-06-91	JP-C- 1856000	07-07-94
		JP-A- 3176064	31-07-91
		AU-B- 6771790	13-06-91
		CA-A- 2031461	06-06-91
EP-A-0477979	01-04-92	JP-A- 4138169	12-05-92
EP-A-0302536	08-02-89	AU-B- 569031	21-01-88
		AU-B- 1356583	27-10-83
		CA-A- 1220422	14-04-87
		DE-A- 3382538	07-05-92
		DE-A- 3382643	24-12-92
		EP-A,B 0092999	02-11-83
		IE-B- 60457	13-07-94
		JP-B- 6013045	23-02-94
		JP-A- 58190446	07-11-83
		US-A- 4538603	03-09-85
		US-A- 4728642	01-03-88